

# Product Data Sheet



## Crimson Granite



Bush Hammered



Flamed

### Description

Appearance  
Finishes  
Governing Standards  
Quarry of Origin

Igneous rock with large crystals set in fine grained groundmass  
Flamed, Fine Picked, Honed or Polished  
BS EN 1343 : 2001  
Fujian P.R.C

### Physical Properties

Work Dimensions	To customers' specification
Tolerances on Dimensions	Class 2
Compressive Strength	201 MPa
Flexural Strength	25 MPa
Material Density	2900kg/m <sup>3</sup> (typically)
Slip Resistance	54 Wet – TLR
Abrasion Resistance	75 Dry – TLR
Water Absorption	19.00mm
	0.12%



### Supply

Crate Size  
Packaging

Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high  
Wooden crates, suitable for stacking and transportation by fork lift.

### Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material.

#### **BBS Granite Concepts Ltd**

Kimcote House, Walton Road,  
Kimcote, Leicestershire  
LE17 5RU  
Tel: 01455 559474  
Email: [sales@bbsgraniteconcepts.com](mailto:sales@bbsgraniteconcepts.com)  
[www.bbsnaturalstone.com](http://www.bbsnaturalstone.com)



**Ethical Trading Initiative**  
Respect for workers worldwide

#### **BBS Brick & Stone Ltd**

Lower Wharfe House,  
Wharfebank Mills, Otley, Yorkshire  
LS21 3JP  
Tel: 01924 241 100  
Email: [sales@bbsgraniteconcepts.com](mailto:sales@bbsgraniteconcepts.com)  
[www.bbsnaturalstone.com](http://www.bbsnaturalstone.com)