

City Blend Sandstone



PRODUCT DESCRIPTION

Appearance	Fine to medium grained buff-coloured sandstone
Petrographic Description	Sandstone
Quarry Location	India
Available Finishes	Sawn, Sandblasted & Flamed
Governing Manufacturing Standards	All data where relevant to be established in accordance with BS EN 1341 : 2002, BS EN 1342 : 2012, BS EN 1343 : 2012

PHYSICAL PROPERTIES

Work Dimensions (mm)	To Customer's Specification	
Tolerances on Dimensions (mm)	Class 2	
Material Density	2590 KG/m ³	BS EN 1936 : 2006
Compressive Strength	217 MPa	BS EN 1926 : 2006
Flexural Strength	Under Concentrated Load: 36.5 MPa	BS EN 12372 : 2006
	After Freeze/Thaw Test (56 Cycles): 29.4 MPa	BS EN 12372 : 2006
Abrasion Resistance	15mm	BS EN 14157 : 2017
Water Absorption	0.9%	BS EN 13364 : 2008
Slip Resistance	97 DRY (Sandblast Finish)	BS EN 14231 : 2003
	77 WET (Sandblast Finish)	
LRV Value	32.68 (Sandblast Finish)	

Cleaning & Maintenance

All stones vary and each one should be assessed on an individual basis. Many are slightly alkali so acidic cleaners/cleaning solutions should be avoided. For further information please contact our technical department.